

U.S. Serial No. 10/678,547  
Reply to Office Action of: October 4, 2006  
Family Number: P2002J111 US2

Page 4

### AMENDMENTS TO THE CLAIMS

1. (Currently amended) A functional fluid having improved viscosity and volatility control under conditions of high thermal stress comprising:

- a) a base stock or base oil, said base stock or base oil having the properties of:
  - (a) a viscosity index (VI) of greater than 130;
  - (b) a pour point of about -10C or lower;
  - (c) a ratio of measured-to-theoretical low-temperature viscosity equal to about 1.2 or less, at a temperature of about -30C or lower, where the measured viscosity is cold-crank simulator viscosity and where theoretical viscosity is calculated at the same temperature using the Walther-MacCoull equation wherein said base stock or base oil is not a Group IV base stock or base oil; ~~and~~
  - (d) a Noack volatility of less than 15 weight percent; and
- b) at least one additive.

2. (Currently amended) A functional fluid having improved viscosity and volatility control under conditions of high thermal stress comprising:

- a) a base stock or base oil, said base stock or base oil having the properties of:
  - (i) a viscosity index (VI) of about 130 or greater;
  - (ii) a pour point of about -10C or lower;
  - (iii) a ratio of measured-to-theoretical low-temperature viscosity equal to about 1.2 or less, at a temperature of about -30C or lower, where the measured viscosity is cold-crank simulator viscosity and where theoretical viscosity is calculated at the same temperature using the Walther-MacCoull equation;
  - (iv) a percent Noack volatility no greater than that calculated by the formula  
$$-6.882\text{Ln}(\text{CCS}@-35\text{C}) + 67.647,$$

U.S. Serial No. 10/678,547

Reply to Office Action of: October 4, 2006

Page 5

Family Number: P2002J111 US2

where  $CCS@-35C$  is the base oil CCS viscosity in centipoise, tested at -35C, and that value as used in the equation is less than 5500 cP and wherein said base stock or base oil is not a Group IV base stock or base oil; and

(v) a Noack volatility of less than 15 weight percent; and

b) at least one additive.

3. (Currently amended) A lubricating oil having improved viscosity and volatility control under conditions of high thermal stress comprising:

a) at least one base stock or base oil wherein said base stock or base oil has a VI of at least 130 produced by a process which comprises:

- (i) hydrotreating a feedstock having a wax content of at least about 60 wt.%, based on feedstock, with a hydrotreating catalyst under effective hydrotreating conditions such that less than 5 wt.% of the feedstock is converted to 650F (343C) minus products to produce a hydrotreated feedstock whose VI increase is less than 4 greater than the VI of the feedstock;
- (ii) stripping the hydrotreated feedstock to separate gaseous from liquid product;
- (iii) hydrodewaxing the liquid product with a dewaxing catalyst which is at least one of ZSM-48, ZSM-57, ZSM-23, ZSM-22, ZSM-35, ferrierite, ECR-42, ITQ-13, MCM-71, MCM-68, beta, fluorided alumina, silica-alumina or fluorided silica alumina under catalytically effective hydrodewaxing conditions wherein the dewaxing catalyst contains at least one Group 9 or Group 10 noble metal; and

b) at least one additive.

U.S. Serial No. 10/678,547

Reply to Office Action of: October 4, 2006

Family Number: P2002J111 US2

Page 6

4. (Currently amended) A functional fluid having improved viscosity and volatility control under conditions of high thermal stress comprising:

- a) at least one base stock or base oil wherein said base stock has a VI of at least 130, a pour point of about -10°C or lower, and a Noack volatility of less than 15 weight percent produced by a process which comprises:
  - (i) hydrotreating a lubricating oil feedstock having a wax content of at least about 50 wt.%, based on feedstock, with a hydrotreating catalyst under effective hydrotreating conditions such that less than 5 wt.% of the feedstock is converted to 650F (343C) minus products to produce a hydrotreated feedstock to produce a hydrotreated feedstock whose VI increase is less than 4 greater than the VI of the feedstock;
  - (ii) stripping the hydrotreated feedstock to separate gaseous from liquid product;
  - (iii) hydrodewaxing the liquid product with a dewaxing catalyst which is at least one of ZSM-22, ZSM-23, ZSM-35, ferrierite, ZSM-48, ZSM-57, ECR-42, ITQ-13, MCM-68, MCM-71, beta, fluorided alumina, silica-alumina or fluorided silica-alumina under catalytically effective hydrodewaxing conditions wherein the dewaxing catalyst contains at least one Group 9 or 10 noble metal; (iv) hydrofinishing the product from step (3) with a mesoporous hydrofinishing catalyst from the M41S family under hydrofinishing conditions; and
- b) at least one additive.

5. (Currently amended) A functional fluid having improved viscosity and volatility control under conditions of high thermal stress comprising:

- a) at least one base stock wherein said base stock has a VI of at least 130, a pour point of about -10°C or lower, and a Noack volatility of less than 15 percent produced by a process which comprises:

U.S. Serial No. 10/678,547

Reply to Office Action of: October 4, 2006

Family Number: P2002J111 US2

Page 7

- (i) hydrotreating a lubricating oil feedstock having a wax content of at least about 60 wt.%, based on feedstock, with a hydrotreating catalyst under effective hydrotreating conditions such that less than 5 wt.% of the feedstock is converted to 650F (343C) minus products to produce a hydrotreated feedstock to produce a hydrotreated feedstock whose VI increase is less than 4 greater than the VI of the feedstock;
  - (ii) stripping the hydrotreated feedstock to separate gaseous from liquid product;
  - (iii) hydrodewaxing the liquid product with a dewaxing catalyst which is ZSM-48 under catalytically effective hydrodewaxing conditions wherein the dewaxing catalyst contains at least one Group 9 or 10 noble metal;
  - (iv) Optionally, hydrofinishing the product from step (3) with MCM-41 under hydrofinishing conditions; and
- b) at least one additive

6. (Original) The functional fluid as in any one of claims 3, 4, or 5, wherein said feedstock is a synthetic gas to liquid feedstock.

7. (Original) The functional fluid as in any one of claims 3, 4, or 5, wherein said feedstock is made by a Fischer-Tropsch process.

8. (Original) A functional fluid of claims 1, 2, 3, 4 or 5 comprising at least one performance enhancing additive.

9. (Original) A functional fluid of claims 1, 2, 3, 4 or 5 comprising at least one performance enhancing additive where said performance enhancing additive is not a viscosity index improver.

U.S. Serial No. 10/678,547  
Reply to Office Action of: October 4, 2006  
Family Number: P2002J111 US2

Page 8

10. (Original) A functional fluid of claims 1, 2, 3, 4 or 5 where said functional fluid is a circulating oil.

11. (Original) A functional fluid of claims 1, 2, 3, 4 or 5 where said functional fluid is a compressor oil.

12. (Original) A functional fluid of claims 1, 2, 3, 4 or 5 where said functional fluid is an internal lubricant for sintered metal materials.

13. (Currently amended) A ~~The~~ method of making a functional fluid having improved viscosity and volatility control under conditions of high thermal stress comprising incorporating a base stock or base oil having the properties of

- (a) a viscosity index (VI) of 130 or greater,
- (b) a pour point of -10C or lower,
- (c) a ratio of measured-to-theoretical low-temperature viscosity equal to 1.2 or less, at a temperature of -30C or lower, where the measured viscosity is cold-crank simulator viscosity and where theoretical viscosity is calculated at the same temperature using the Walther-MacCoul equation-

(d) a Noack volatility of less than 15 weight percent

wherein said base stock or base oil is not a Group IV base stock or base oil.

14. (Currently amended) A ~~The~~ method of making a functional fluid having improved viscosity and volatility control under conditions of high thermal stress comprising incorporating a base stock or base oil having the properties of

- (a) a viscosity index (VI) of 130 or greater,
- (b) a pour point of -10C or lower,

U.S. Serial No. 10/678,547

Reply to Office Action of: October 4, 2006

Page 9

Family Number: P2002J111 US2

(c) a ratio of measured-to-theoretical low-temperature viscosity equal to 1.2 or less, at a temperature of -30C or lower, where the measured viscosity is cold-crank simulator viscosity and where theoretical viscosity is calculated at the same temperature using the Walther-MacCoull equation, and

(d) a percent Noack volatility no greater than that calculated by the formula

$$-6.882\text{Ln}(\text{CCS@-35C}) + 67.647,$$

where CCS@-35C is the base oil CCS viscosity in centipoise, tested at -35C,

and that value as used in the equation is less than 5500 cP, and

wherein said base stock or base oil is not a Group IV base stock or base oil.

(c) a Noack volatility of less than 15 weight percent.

15. (Original) A method of reducing the Noack volatility of a functional fluid comprising incorporating said base stock or base oil of any one of the claims 1, 2, 3, 4 or 5.